

**Fire-Rated Glass Ceramic**  
**Fire-Rating: 20-90 Minutes (180 Minutes\*)**

FireLite is a 3/16" (5 mm) thick fire-rated glazing material. It is listed for use in non-impact safety-rated locations such as transoms and borrowed lites.

**FEATURES**

- ultraHD® Technology for improved surface quality, clarity and color
- Fire-rated for up to 90 minutes with required hose stream test (180 minutes\*)
- Clear and wireless glass ceramic
- Fits in Fireframes® Designer Series frames from TGP, or standard fire-rated frames
- Withstands thermal shock
- Large sizes available
- May be lightly sandblasted or etched on one side without affecting fire rating
- May be insulated (see FireLite IGU fact sheet)

**Notes:**

1. This product is not a barrier to radiant heat, as it does not meet test standards ASTM E119 or UL 263. If your jurisdiction requires a "barrier to heat" product, please contact TGP regarding Fireglass®.
2. FireLite is not an impact safety-rated product and should not be specified as such. However, TGP does offer FireLite Plus® and FireLite® NT which carry both fire and impact safety ratings. Please contact TGP for more details.

**LISTINGS/STANDARDS**

Classified and labeled by Underwriters Laboratories, Inc.® and Underwriters Laboratories of Canada. File number for labeled fire-rated assemblies is R13377. FireLite products have been tested to BS 476-20 up to 3 hours for 1.21 m x 2.43 m and .91 m x 2.43 m dimensions. Tests performed in accordance with:


UL 9	NFPA 80	CAN/ULC-S104	BS 476-20
UL 10B	NFPA 257	CAN/ULC-S106	
UL 10C			

\*For Warnock Hersey | Intertek listed products, tested to BS 476 Part 22 (1987), EN 1364-1 (2015), BS 476 Part 20 (1987), EN1634-1:2014+A1(2018), see spec ID 50721 and/or certificate number WHI19-33395001 for specific sizes and limitations.

**MAXIMUM EXPOSED AREA**


RATING	ASSEMBLY	MAX. EXPOSED AREA	MAX. WIDTH OF EXPOSED GLAZING	OR	MAX. HEIGHT OF EXPOSED GLAZING
20 to 60 min.	OTHER THAN DOORS	3,325 in <sup>2</sup> / 23.09 ft <sup>2</sup> (2.15 m <sup>2</sup> )	95" (2,413 mm)		95" (2,413 mm)
90 min.	OTHER THAN DOORS	2,627 in <sup>2</sup> / 18.24 ft <sup>2</sup> (1.69 m <sup>2</sup> )	56-1/2" (1,435 mm)		56-1/2" (1,435 mm)


Check with frame manufacturer for maximum tested glass sizes and required stop height.  
**Note: Individual lite sizes cannot exceed "Max. Exposed Area" shown above.**


 BIM 3D Model Available


---


**ultraHD**  
TECHNOLOGY

 UL Classified & Labeled

 Intertek Listed & Labeled

 Fire-Rated

 Hose Stream Tested

 Positive Pressure Tested

## MAXIMUM SHEET SIZE

<b>SURFACE FINISH</b>	48" x 96" (1.21 m x 2.43 m)	36" x 96" (.91 m x 2.43m)
-----------------------	--------------------------------	------------------------------

## GENERAL CHARACTERISTICS

THICKNESS:	3/16" (5 mm) overall
WEIGHT:	2.56 lb / ft <sup>2</sup> (12.5 kg / m <sup>2</sup> )
APPROX. VISIBLE TRANSMISSION:	88%
APPROX. VISIBLE REFLECTION:	9%
HARDNESS (VICKER'S SCALE):	700
FIRE RATING:	20 to 90 minutes (180 minutes*)
IMPACT SAFETY RATING:	None
STC RATING:	35

## LABELING

Each piece of FireLite shall be permanently labeled with the FireLite logo, UL logo and fire rating.

## INSTALLATION

FireLite shall be glazed into the appropriate fire-rated framing with an approved glazing compound (pure silicone, closed cell PVC tape or DAP 33 putty) as supplied by the installer. For 90 minute ratings or greater that exceed 1,393 in<sup>2</sup> (.8987 m<sup>2</sup>) FireLite shall be glazed with fire-rated glazing tape as supplied by TGP.

Inspect each piece of FireLite immediately before installation and eliminate any with observable edge damage or face imperfections. As with any glass produced by the "roll out" method, individual pieces of FireLite may contain minimal variations in thickness. Occasionally, process marks and small occlusions or seeds (bubbles, knots or crystals) may be apparent. However, since they do not generally impair the transparency or affect the technical performance of the glass, they do not represent cause for rejection.

## STORAGE & HANDLING

FireLite must be handled with care during transportation, storage, inspection and installation. Store in a dry place.

## FAMILY OF PRODUCTS

TGP offers a complete family of products for all your fire-rated glazing needs, ranging from 20 minute to 3 hour applications. More information is available online at [fireglass.com](http://fireglass.com).

